



# The Monarch Cement Company

449 1200 Street · PO Box 1000 · Humboldt, KS 66748  
 Phone: 620-473-2222 · Fax: 620-473-2447

## Certified Mill Test Report - Type I/II

**Production Period:** March 1, 2018 through March 31, 2018

The following is based on average test data during the production period. The data is typical of cement produced at The Monarch Cement Company, Humboldt, KS. Individual shipments may vary.

### PHYSICAL

	<u>Reported</u>	<u>Spec Limit</u>		<u>Reported</u>	<u>Spec Limit</u>
325 Sieve, % Passing	96.9	-	Air Content of Mortar (volume %)	7.3	<b>12.0 max</b>
Blaine fineness, specific surface			Autoclave Expansion (%)	-0.029	<b>0.80 max</b>
Air Permeability (cm <sup>2</sup> /g)	3560	<b>2600 min</b>	Compressive Strength (psi)		
Time of Setting, Gilmore test:			1 Day	2430	-
Initial (hrs:min)	2:40	<b>60 min</b>	3 Days	3740	<b>1740 min</b>
Final (hrs:min)	4:10	<b>600 max</b>	7 Days	4995	<b>2760 min</b>

### CHEMICAL

	<u>Reported</u>	<u>Spec Limit</u>		<u>Reported</u>	<u>Spec Limit</u>
SiO <sub>2</sub> - Silicon dioxide (%)	21.34	-	Loss on ignition (%)	2.04	<b>3.0 max</b>
Fe <sub>2</sub> O <sub>3</sub> - Ferric oxide (%)	2.85	<b>6.0 max</b>	Insoluble residue (%)	0.39	<b>1.50 max</b>
Al <sub>2</sub> O <sub>3</sub> - Aluminum oxide (%)	4.46	<b>6.0 max</b>	Free lime (%)	1.10	-
CaO - Calcium oxide (%)	64.69	-	Na <sub>2</sub> O - Sodium oxide (%)	0.19	-
MgO - Magnesium oxide (%)	1.37	<b>6.0 max</b>	K <sub>2</sub> O - Potassium oxide (%)	0.55	-
SO <sub>3</sub> - Sulphur trioxide (%)	2.65	<b>3.0 max</b>	Equivalent Alkalies (%)	0.55	<b>0.60 max</b>
			Inorganic Processing Addition (%)	2.10	<b>5.0 max</b>

### POTENTIAL CALCULATED COMPOUNDS

C <sub>3</sub> S - Tricalcium silicate (%)	59.6	-
C <sub>2</sub> S - Dicalcium silicate (%)	16.2	-
C <sub>3</sub> A - Tricalcium aluminate (%)	7.0	<b>8 max</b>
C <sub>4</sub> AF - Tetracalcium aluminoferrite (%)	8.7	-

### INORGANIC PROCESS ADDITON (C150)

Process Dust (%)	2.10
SiO <sub>2</sub> - Silicon dioxide (%)	10.3
Fe <sub>2</sub> O <sub>3</sub> - Ferric oxide (%)	2.16
Al <sub>2</sub> O <sub>3</sub> - Aluminum oxide (%)	4.23
CaO - Calcium oxide (%)	43.8
SO <sub>3</sub> - Sulphur trioxide (%)	0.46

The cement in this shipment meets standard requirements in the current specifications of the Federal Government and the American Society for Testing and Materials for Type I and for Type II Portland Cement. All tests conform to AASHTO M-85 and ASTM Test Methods: Chemical C-114, Blaine C-204, Soundness C-151, Gillmore C-266, Compressive Strength C-109, Air Content C-185, C-465 and C-150.

Date: 4/12/2018

Sean D. Bowman  
 Quality Control Supervisor