



The Monarch Cement Company

449 1200 Street · PO Box 1000 · Humboldt, KS 66748
Phone: 620-473-2222 · Fax: 620-473-2447

Certified Mill Test Report - Masonry Type - S

Production Period: June 1 - June 30, 2018

The following is based on average test data during the production period. The data is typical of cement produced at The Monarch Cement Company, Humboldt, KS. Individual shipments may vary.

	ASTM C91	MONARCH
Fineness, residue on No 325 sieve (45 micron)		
Maximum %.....	24	2.2
Autoclave Expansion - - Maximum %	1	0.004
Gillmore Time of Setting, Initial.....	1.5	1:50
Compressive Strength - - PSI		
7 Days.....	1300	2400
28 Days.....	2100	2790
Air Content of Mortar		
Minimum %.....	8	16.2
Maximum %.....	19	
Water Retention - -		
Minimum % of original flow	70	90

The cement in this shipment meets standard requirements in the current specifications of the Federal Government and the American Society for Testing and Materials . All tests conform to ASTM Test Methods: Chemical C-114, Blaine C-204, Soundness C-151, Gillmore C-266, Compressive Strength C-109, Air Content C-185, and C-91.

Date: 8/10/2018

Sean D. Bowman
Quality Control Supervisor